

EXHIBIT A



(12) **EUROPEAN PATENT SPECIFICATION**

(45) Date of publication and mention
of the grant of the patent:
30.08.2006 Bulletin 2006/35

(21) Application number: **03796078.8**

(22) Date of filing: **03.12.2003**

(51) Int Cl.:
C08L 53/02 (2006.01)

(86) International application number:
PCT/EP2003/050931

(87) International publication number:
WO 2004/052989 (24.06.2004 Gazette 2004/26)

(54) **STYRENIC BLOCK COPOLYMER COMPOSITIONS TO BE USED FOR THE MANUFACTURE OF TRANSPARENT, GEL FREE FILMS.**

**ZUSAMMENSETZUNGEN VON STYRENBLOCKCOPOLYMEREN FÜR DIE HERSTELLUNG
TRANSPARENTER GELFREIER FOLIEN**

**COMPOSITIONS DE POLYMÈRES À BLOCS DE STYRÈNE POUR LA PRÉPARATION DE FILMS
TRANSPARENTS EXEMPTS DE GEL**

(84) Designated Contracting States:
DE FR GB IT NL

(30) Priority: **06.12.2002 EP 02027269**

(43) Date of publication of application:
07.09.2005 Bulletin 2005/36

(73) Proprietor: **KRATON Polymers Research B.V.**
1030 BH Amsterdam (NL)

(72) Inventors:

- **JOLY, Gert,**
Kraton Polymers Research S.A.
1348 Ottignies-Louvain-La-Neuve (BE)
- **MOERENHOUT, Jaak L.,**
Kraton Polymers Research S.A.
1348 Ottignies-Louvain-La-Neuve (BE)

(56) References cited:

EP-A- 0 921 153 WO-A-01/04208
US-A- 6 050 871 US-A1- 2002 001 707

EP 1 569 999 B1

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

DescriptionField of the invention

5 [0001] The present invention relates to styrenic block copolymer compositions to be used for the manufacture of transparent, gel free films.

[0002] More in particular the invention relates to styrenic block copolymer compositions which comprise a styrenic block copolymer, comprising at least one central block obtainable by at random copolymerization of predominantly isoprene and butadiene, to be used for the manufacture of mono- or multilayer films for application in the personal hygiene industry and showing an improved quality.

Background of the invention

15 [0003] Elastomeric compositions which can be easily extruded into elastic films having low stress relaxation, low hysteresis or permanent set, and high recoverable energy are known from e.g. US patents nos 4,663,220; 4,789,699; 4,970,259; 5,093,422; 5,705,556.

[0004] Processes for making cast extruded films and extrusion blown films have to meet high requirements as to the viscosity of the composition.

20 [0005] At the same time, applications of these extrudates in personal hygiene are related to stringent requirements on mechanical behaviour, i.e. combination of stiffness (high modulus) and excellent elasticity (good stress relaxation and low hysteresis and permanent set) is needed.

[0006] One of the greatest challenges in this field is still to find a good balance between flow/viscosity and the mechanical properties mentioned above.

25 [0007] It is an object of the present invention to provide compositions, have an improved balance of properties in personal hygiene applications and more in particular have an improved balance of properties of compositions for mono- or multi-layer films, i.e. compositions showing a higher melt flow rate (MFR) providing softer, transparent films without fines/fish eyes/gels, in combination with lower tensile strength and lower modulus and lower set.

Summary of the invention

30 [0008] Accordingly a composition is provided which can be used for the manufacture of transparent, gel free films, comprising:

35 a) at least 65 wt% of a styrenic block copolymer, having a molecular structure according to the formula S-(I/B)-S (1) or [S-(I/B)]_n X (2), wherein each S independently is a polymer block of predominantly styrene and (I/B) is a substantially random polymer block of predominantly isoprene and butadiene in a mutual weight ratio in the range of from 30/70 to 70/30, wherein said polymer block (I/B) has a glass transition temperature (T_g) of at most -60°C (determined according to ASTM E-1356-98), wherein n is an integer equal to or greater than 2, and wherein X is the residue of a coupling agent, wherein said styrenic block copolymer having a poly (styrene) content in the range of from 28 to 31 % by weight, having poly(styrene) blocks S of a true molecular weight in the range of from 10,000 to 15,000, having an apparent molecular weight of the complete block copolymer in the range of from 110,000 to 160,000 and wherein the diblock S-(I/B) optionally occurs in a content of at most 20 mole%,

40 b) from 5 to 25 wt% of a thermoplastic resin, which is different from component (a),

45 c) from 0 to 10 wt% of a plasticizing oil, the sum of the percentages of the components a, b and c being 100%, and all weight percentages being relative to the weight of the complete composition.

[0009] It will be appreciated that another aspect of the invention is formed by extruded mono- or multi-layer films and more in particular by cast or blown mono- or multi-layer films for personal hygiene applications, prepared from the hereinbefore specified compositions.

Detailed description of the invention

[0010] Compositions according to the present invention comprise at least 65 wt% of at least one block copolymer of the formulae S-(I/B)-S or [S-(I/B)]_n X and are derived from predominantly isoprene and butadiene.

55 [0011] Preferably said compositions comprise said block copolymer in weight proportions of from 70 to 90 wt%.

[0012] In preferred compositions, the mutual weight ratio between isoprene and butadiene in the I/B blocks is in the range of from 40/60 to 60/40 wt% and more preferably from 45/55 to 55/45 wt% and most preferably from 48/52 to 52/48 wt%.

[0013] With the terms "predominantly styrene" and "predominantly butadiene" respectively, as used throughout the specification, are meant that for the respective blocks to be prepared, substantially pure styrene or mixtures comprising at least 95 wt% of styrene and minor amounts of other comonomers can be used, and substantially pure butadiene or mixtures comprising at least 95 wt% of butadiene and minor amounts of other comonomers, can be used.


[0014] The small proportions of other comonomers in the polystyrene blocks can consist of structurally related comonomers such as alpha-methyl styrene, p-methyl styrene, o-methyl styrene, p-tert-butyl styrene, dimethyl styrene and vinyl naphthalene, or butadiene and/or isoprene.

[0015] The small proportions of other comonomers in the poly(isoprene/butadiene) block can consist of styrene and/or structurally related alkadienes.

[0016] However, preferred block copolymers to be applied according to the present invention contain blocks of substantially pure styrene and mixtures of substantially pure isoprene and butadiene.

[0017] The block copolymer according to the present invention may be branched or linear and may be a triblock, tetrablock or multiblock.

[0018] It has a structure represented by the general formulae



wherein each S independently is a polymer block of predominantly styrene and (I/B) is a copolymer block of substantially at randomly polymerized mixtures of isoprene and butadiene, in a mutual weight ratio in the range of from 40/60 to 60/40 wt% and preferably from 45/55 to 55/45 wt% and more preferably from 48/52 to 52/48 wt%, wherein said (I/B) block has a glass transition temperature (T_g) of at most -60°C and preferably in the range of from -85 to -75°C (determined according to ASTM E-1356-98), wherein n is an integer equal to or greater than 2, and wherein X is the residue of a coupling agent.

[0019] The polymer blocks S have a true molecular weight in the range of from 10,000 to 15,000 and preferably from 10,500 to 14,800.

[0020] Preferred block copolymers to be used in the compositions of the present invention have apparent total molecular weights in the range of from 115,000 to 155,000.

[0021] The poly(styrene) content (PSC) in said block copolymers is in the range of from 28 to 31 wt% and preferably from 29 to 30 wt%.

[0022] The block copolymers to be used according to the present invention preferably contain 1,2-vinyl bonds and/or 3,4 vinyl bonds in a proportion of at most 15 wt%, based on the weight of conjugated diene and preferably of at most 10 wt%.

[0023] The block copolymers according the present invention preferably have a storage modulus (G') of from 1 to 10 MPa in a viscoelasticity measurement, in a temperature (T) range of from 0 to 50°C, and only one peak on loss tangent (tan δ) attributable to the mixed isoprene/butadiene polymer block at a temperature of -55°C or below.

[0024] With the term "substantially at random polymerized mixtures of isoprene and butadiene" is actually meant that the central (I/B) blocks only contain average homopolymer block lengths of less than 100 monomer units and preferably of less than 50 monomer units and more preferably of less than 20 monomer units.

[0025] Said average homopolymer block length may be determined by various methods.

[0026] The method used in the present application is based on carbon-13 NMR and said method has been disclosed in detail in WO 02/057386A, pages 12, 13, 14 and 15.

[0027] The block copolymers according to the present invention can be prepared by full sequential polymerization of predetermined batches of predominantly styrene monomer, of isoprene/butadiene mixtures and of predominantly styrene respectively (for triblock copolymers S-(I/B)-S) by anionic polymerization in an inert organic solvent, or by coupling of an initially prepared living diblock copolymer, obtained by sequential polymerization of predetermined batches of predominantly styrene and of predominantly isoprene/butadiene by anionic polymerization in an inert organic solvent, with a coupling agent (to provide triblock or multiblock copolymers).

[0028] In both preparation methods the remaining living block copolymers have to be terminated by addition of a proton donating agent, such as an alkanol, e.g. ethanol or water.

[0029] It will be appreciated that block copolymers, prepared by means of coupling of living diblock copolymers by means of a coupling agent and termination of remaining living block copolymers, will finally contain small amounts (i.e. less than 20 mole% and preferably less than 15 mole% and more preferably less than 10 mole%) of diblock copolymer, having the same S blocks (mole% relative to the weight of the total block copolymer).

[0030] As examples of the coupling agent may be mentioned tin coupling agents such as tin dichloride, monomethyltin dichloride, dimethyltin dichloride, monoethyltin dichloride, diethyltin dichloride, methyltin trichloride, monobutyltin dichloride, dibutyltin dibromide, monohexyltin dichloride and tin tetrachloride; halogenated silicon coupling agents such as dichlorosilane, monomethyldichlorosilane, dimethyldichlorosilane, diethyldichlorosilane, monobutyldichlorosilane, dibutyldichlorosilane, monohexyldichlorosilane, dihexyldichlorosilane, dibromosilane, monomethyldibromosilane, dimethyldibromosilane, silicon tetrachloride and silicon tetrabromide; alkoxysilanes such as tetramethoxysilane; divinyl aromatic compounds such as divinylbenzene or divinyl naphthalene; halogenated alkanes such as dichloroethane, dibro-

moethane, methylene chloride dibromomethane, dichloropropane, dibromopropane, chloroform, trichloroethane, trichloropropane and tribromopropane; halogenated aromatic compounds such as dibromobenzene; epoxy compounds such as the diglycidyl ether of bisphenol-A (e.g. EPON 825 or EPON 826, a trademark), and other coupling agents such as benzoic esters, CO₂, 2-chloroprene and 1-chloro-1,3-butadiene and diethyladipate or dimethyladipate.

[0031] Of these EPON 825, diglycidyl ethers, dibromobenzene, tetramethoxysilane and dimethyldichlorosilane are preferred.

[0032] The apparent molecular weights of the complete block copolymers and each of the intermediate precursors have been determined by Gel Permeation Chromatography, and expressed in terms of standard poly(styrene), by using the method described:- ASTM D 3536.

[0033] In general, the polymers useful in this invention may be prepared by contacting the monomer or monomers with an organoalkali metal compound in a suitable solvent at a temperature within the range from -150°C to 300°C, preferably at a temperature within the range from 0°C to 100°C. Particularly effective polymerization initiators are organolithium compounds having the general formula

RLi

wherein R is an aliphatic, cycloaliphatic, alkyl-substituted cycloaliphatic, aromatic or alkyl-substituted aromatic hydrocarbon radical having from 1 to 20 carbon atoms of which sec.butyl is preferred.

[0034] Suitable solvents include those useful in the solution polymerization of the polymer and include aliphatic, cycloaliphatic, alkyl-substituted cycloaliphatic, aromatic and alkyl-substituted aromatic hydrocarbons, ethers and mixtures thereof. Suitable solvents, then, include aliphatic hydrocarbons such as butane, pentane, hexane and heptane, cycloaliphatic hydrocarbons such as cyclopentane, cyclohexane and cycloheptane, alkyl-substituted cycloaliphatic hydrocarbons such as methylcyclohexane and methylcycloheptane, aromatic hydrocarbons such as benzene and the alkyl-substituted hydrocarbons such as toluene and xylene, and ethers such as tetrahydrofuran, diethylether and di-n-butyl ether. Preferred solvents are cyclopentane or cyclohexane.

[0035] The block copolymers according to the general formulae (1) and (2) can be made by mere adaptation of common processes used for the preparation of S-B-S type block copolymers and/or S-I-S type block copolymers, using a mixture of butadiene/isoprene instead. Of importance in the preparation of the block copolymers according to the present invention is to avoid homopolymer block formation, to ensure appropriate B/I ratio, and to produce a polymer block wherein the random midblock has a T_g of -60°C or less. This generally rules out the use of randomizers, as for instance used by Kuraray in the production of hydrogenated styrene isoprene/butadiene block copolymers (reference is made to US patent 5,618,882 which is incorporated herein).

[0036] It may also be beneficial to adapt the process by adding one or both comonomers during the formation of the mixed midblock.

Component (b)

[0037] The second different thermoplastic polymer component (b) may be selected from the group of polyolefins, polystyrene resins, coumarone-indene resins, polyindene resins, poly(methylindene) resins, alpha-methylstyrene resins, polyphenylene resins (and in particular poly(2,6-dimethyl-1,4-phenylene ether) or mixtures of said resins or copolymers of styrene and other compatible comonomers such as alpha methyl styrene, methyl styrene, vinyl toluene.

[0038] Suitable examples of poly(olefin) resins are poly(ethylene), polypropylene or copolymers of ethylene, propylene, alone or with other comonomers such as EPDM.

[0039] Examples of poly(ethylene) are HDPE, LDPE, LLDPE. Ethylene or propylene polymers prepared with metallocene catalysts can also be used.

[0040] Preferred components (b) are polystyrenes, having a high molecular weight (i.e. greater than 30,000) clear poly(styrene), toughened poly(styrene) or other poly(styrene) homopolymers or copolymers of styrene and other compatible comonomers, such as alpha methyl styrene, methyl styrene, vinyl toluene, or blends of polystyrene and poly(phenylene) resins.

[0041] A more preferred component (b) is PS 144c poly(styrene) resin of BASF. Said polystyrenes provide in the compositions of the present invention films, which are transparent and water-white.

[0042] The composition preferably comprises from 8 to 12 %w of the second different polymer, relative to the weight of the complete composition.

Component (c)

[0043] Suitable plasticizers include plasticizing oils like low aromatic content hydrocarbon oils that are paraffinic or naphthenic in character (carbon aromatic distribution < 5%, preferably < 2%, more preferably 0% as determined according

to DIN 51378). Those products are commercially available from the Royal Dutch/Shell Group of companies, like SHELL-FLEX, CATENEX, and ONDINA oils. Other oils include KAYDOL oil from Witco, or TUFFLO oils from Arco or PRIMOL oils from EXXON-MOBIL. Other plasticizers include compatible liquid tackifying resins like REGALREZ R-1018. (SHELL-FLEX, CATENEX, ONDINA, KAYDOL, TUFFLO, PRIMOL and REGALREZ are trademarks).

[0044] Other plasticizers may also be added, like olefin oligomers; low molecular weight polymers ($< 30,000$ g/mol) like liquid polybutene, liquid polyisoprene copolymers, liquid styrene/isoprene copolymers or liquid hydrogenated styrene/conjugated diene copolymers; vegetable oils and their derivatives; or paraffin and microcrystalline waxes.

[0045] More preferably the plasticizer represents a plasticizing oil selected from paraffinic or naphthenic oils, in an amount of from 4 to 6 wt%, relative to the weight of the complete composition.

Additional auxiliaries

[0046] Other rubber components may be incorporated into the adhesive compositions according to the present invention. It is also known in the art that various other components can be added to modify the tack, the odor, the color of the present compositions and of the resulting film. Antioxidants and other stabilizing ingredients can also be added to protect the composition of the present invention from degradation induced by heat, light and processing or during storage.

[0047] Several types of antioxidants can be used, either primary antioxidants like hindered phenols or secondary antioxidants like phosphite derivatives or blends thereof. Examples of commercially available antioxidants are IRGANOX 565 from Ciba-Geigy (2,4-bis-(n-octylthio)-6-(4-hydroxy-3,5-di-tertiary-butyl anilino)-1,3,5-triazine), IRGANOX 1010 from Ciba-Geigy (tetrakis-ethylene-(3,5-di-tertiary-butyl-4-hydroxyhydrocinnamate)methane) and POLYGARD HR from Uniroyal (tris-(2,4-di-tertiary-butyl-phenyl)phosphite). Other antioxidants developed to protect the gelling of the polybutadiene segments can also be used, like the SUMILIZER GS from Sumitomo (2[1-(2-hydroxy-3,5-di-ter-pentylphenyl)ethyl]-4,6-di-ter-pentylphenylacrylate); SUMILIZER T-PD from Sumitomo (pentaerythryltetrakis(3-dodecylthiopropionate)); or mixtures thereof. (IRGANOX, POLYGARD and SUMILIZER are trademarks).

Preparation of the composition

[0048] No particular limitation is imposed on the preparation process of the compositions according to the present invention for the manufacture of films.

[0049] Therefore, there may be used any process such as a mechanically mixing process making use of rolls, a Banbury mixer or a Dalton kneader, or twin-screw extruder, thereby obtaining an intimate solution of the composition aimed at.

Use of the composition

[0050] The composition according to the present invention is used for the manufacture of transparent, gel free and preferably water-white, cast extruded or extrusion blown films, the combination of mechanical of which and the viscosity of the composition under processing conditions, has been found to be very attractive.

[0051] More in particular the composition shows an improved balance of properties of films in personal hygiene applications, i.e. a combination of higher melt flow rate (MFR) and providing softer transparent water-white mono-or multi-layer films showing lower tensile strength, low modulus, lower set and no fines/fish eyes/gels.

[0052] The present invention will hereinafter be described more specifically by reference to the following examples and comparative examples, however without restricting its scope to these specific embodiments.

[0053] Incidentally, all designations of "parts" and "%" as will be used in the following examples mean parts by weight and wt% unless expressly noted otherwise.

Examples

[0054] Synthesis of block copolymers A and B. Cyclohexane, styrene, butadiene and isoprene were purified by activated aluminiumoxide and stored at 4°C under a nitrogen atmosphere.

[0055] Dibromoethane (EDB) was used as coupling agent.

[0056] Prior to the synthesis, a monomer mixture of butadiene and isoprene (at a weight/weight ratio given in Table 1) was prepared and stored under nitrogen at 4°C.

[0057] An autoclave, equipped with a helical stirrer, was charged with cyclohexane and the content was heated to a temperature in the range from 50 to 60°C.

[0058] As initiator sec. BuLi was dosed, immediately followed by styrene monomer, which was allowed to polymerize to completion. The reaction temperature was increased to 70°C, at which temperature a isoprene/butadiene monomer mixture (I/B) was dosed and reacted.

[0059] The resulting diblock was either coupled with an excess EDB or further reacted with an additional batch of styrene monomer (full sequential polymerization for S-(I/B) -S triblock copolymer).

[0060] The excess of coupling agent was optionally scavenged with sec-BuLi and followed by addition of ethanol as terminator, or the living triblock copolymer was terminated by addition of ethanol

[0061] The reaction mixture was cooled to 40°C, transported to a blending vessel and a stabilization package was added (comprising IRGANOX 565 and tris(nonylphenol)phosphate 0.08/0.35 phr as a cyclohexane solution) and stirred at ambient temperature.

[0062] Dry block copolymer was obtained by steam coagulation finishing, followed by drying in an oven.

[0063] The polymer was analyzed by GPC according to the method described in US Patents nos. 5,516,824 and 5,499,409, which are herein incorporated by reference. The results of GPC analysis have been listed in Table 1

Table 1

Polymer	A	B
Mw poly(styrene) *10 ³	14.8	10.9
Mw Total blockcopol *10 ³	153	117
Coupling efficiency %	86	
Poly(styrene content)	29.5	30.0
I/B ratio	50/50	50/50
Vinyl in B wt%	8	8
Vinyl in I wt%	5	5

[0064] The average homopolymer block lengths in the (I/B) blocks have been determined by ¹³C NMR, using the method as disclosed in WO02/057386.

[0065] ¹³C NMR spectra of polymer samples were obtained with a Bruker AMX-500 FT spectrometer operating at 125 MHz. Quantitative proton-decoupled spectra were recorded with a 90° ¹³C excitation pulse and a repetition rate of 10 s. 10% (w/w) of polymer solutions in CDCl₃ were used. To improve the relaxation time, 0.1 mol/l chromium acetyl acetonate was added. The applied line broadening was 2 Hz. The spectra were referenced such that the aliphatic carbons of trans.polybutadiene are at 31.9 ppm.

[0066] The polystyrene content was determined by ¹H NMR. Glass transition temperatures T_g have been determined by Differential Scanning Calorimetry with a temperature sweep of 40°C/min.

[0067] The T_g is measured at the onset of the transition. The details of the additional components used in these specified compositions, have been listed in table 2. Compositions for the preparation of cast films were prepared by mixing the components as listed in Table 3 in a Werner & Pfleiderer twin-screw extruder, while also the relevant physical properties of the compositions have been specified in said table 3.

Table 2

KRATON® D 1152 ES	is a linear styrene-butadiene-styrene block copolymer with a PSC of 29.5 %, a total molecular weight of 122,000 and a coupling efficiency of 83%
KRATON® D 1161 NS	is a linear styrene-isoprene-styrene block copolymer with a PSC of 15 %, a total molecular weight of 220,000 and a coupling efficiency of 81%
KRATON® D 1102 CS	a linear styrene-butadiene-styrene block copolymer with a PSC of 29.5 %, a total molecular weight of 127,000 and a coupling efficiency of 84%.
BASF PS 144c	a homo poly(styrene) polymer
PRIMOL™ 352	is a paraffinic oil
IRGANOX™ 565	is an antioxidant from CIBA-GEIGY
EPOLENE™ C-10	is a low density poly(ethylene) from EASTMAN
DOWLEX™ SC 2107	is a linear low density poly(ethylene) from DOW CHEMICAL

Table 3

Examples	I	II	III	IV	V	VI	VII	VIII	IX	X	comparative examples			
											I	II	III	IV
Blockcopolymer A	70	70	85	90	85	90	85	90	85	90				
Blockcopolymer B														
KRATON D-1152ES														
KRATON D-1102CS														
KRATON D-1161NS	15	20									70		70	70
BASF PS 144c	10	10	10	10	10	10			10	10	15	15	20	20
Epofene C-10											10	10	10	10
Dowlex SC2107														
Primal 352	5		5		5		10	10						
Irganox 565	1	1	1	1	1	1	5	5	5	1	5	5		
											1	1		1
MFR (200°C/5kg)	21.7	12	14.5	6	23	12.5	11.5	6.5	22	12.5	13.5	18	9.5	11.5
Cast film results	transparent average amount/ size gels	transparent no gels; best	transparent no gels - best	transparent no gels - best	opaque orange skin	opaque orange skin	slightly opaque orange skin				transparent small amount gels; 3rd best	transparent yellow many gels; worst	transparent small amount gels; 2nd best	transparent yellow little gels
mod. 100% (MPa)	1.22	1.62	1.83	2.78	1.99	2.25	2.22	2.57	1.75	2.22	1.39	1.68	1.78	2
mod. 200% (MPa)	1.52	1.87	2.26	3.48	2.10	2.4	2.46	2.87	2.28	2.91	1.74	2.06	2.22	2.42
mod. 300% (MPa)	1.85	2.22	2.64	4.13	2.26	2.58	2.68	3.24	3.05	3.66	2.14	2.51	2.72	2.91
mod. 500% (MPa)	2.72	3.01	3.43	5.14	2.51	2.83	3.06	3.66	5.48	6.13	3.2	3.68	3.93	4.19
TS (MPa)	5.1	5.4	6.2	9.2	5.1	>8	>8	>14	11.7	21.4	6.8	7.5	8.0	11.9
EB (%)	1170	1520	1710	1725	1655	>2000	>2000	>2000	1435	1800	1420	1245	1520	1730
1st hysteresis (%)	52.5	63.8	55.6	57.2	61.7	65.3	61.0	62.5	28.4	39.0	51.9	50.1	58.6	54.0
2nd hysteresis (%)	36.5	44.0	33.8	33.4	34.2	36.7	34.5	36.3	16.0	19.3	35.8	33.6	39.1	35.0
set (%)	5.8	10.7	4.5	4.8	5.7	6.3	5.5	5.7	4.3	5.6	7.1	8.0	9.1	8.4

Test methods**[0068]**

- 5 • Melt flow rate (MFR): ASTM D 1238-95 (230°C, 2.16 kg)
 • Tensile properties according to ASTM D 882-81 (tested on films)
 • Hysteresis: films are elongated to 80% extension at a speed of 100 mm/sec (load step) held for 30 sec. and then relaxed to zero force (unload step). A second cycle follows right after the first one. Hysteresis is measured as the difference in energy between the load and unload step. Permanent set is measured as the difference between the original sample length of the first cycle (force equals zero) and the sample length before the second cycle (force equals zero).

15 **[0069]** It will be appreciated from the results in Table 3 that the use of the block copolymers A and B (S-(I/B)-S) in compositions I-X, provides an improved processing stability, an improved film quality and at least equal mechanical properties, as compared to compositions, comprising blends of SBS and SIS block copolymers.

Claims

- 20 1. A composition to be used for the manufacture of transparent, gelfree films, comprising:
- a) at least 65 wt% of a styrenic block copolymer, having a molecular structure according to the formula S-(I/B)-S (1) or [S-(I/B)]_n X (2), wherein each S independently is a polymer block of predominantly styrene and (I/B) is a substantially random polymer block of predominantly isoprene and butadiene in a mutual weight ratio in the range of from 30/70 to 70/30, wherein said polymer block (I/B) has a glass transition temperature (T_g) of at most -60°C (determined according to ASTM E-1356-98), wherein n is an integer equal to or greater than 2, and wherein X is the residue of a coupling agent, wherein said styrenic block copolymer having a poly(styrene) content in the range of from 28 to 31 % by weight, having poly(styrene) blocks S of a true molecular weight in the range of from 10,000 to 15,000, having an apparent molecular weight of the complete block copolymer in the range of from 110,000 to 160,000 and wherein the diblock S-(I/B) optionally occurs in a content of at most 20 mol%,
- b) from 5 to 25 wt% of a second thermoplastic resin,
- c) from 0 to 10 wt% of a plasticizing oil, the sum of the percentages of the components a, b and c being 100%, and all weight percentages being relative to the weight of the complete composition.
- 35 2. A composition according to claim 1, wherein the component (a) occurs in a weight proportion of from 70 to 90 wt%.
3. A composition according to claim 1, wherein polymer block (I/B) has average homopolymer block length PB, respectively PI of less than 100 monomer unite, preferably less than 50 monomer units and more preferably less than 20 monomer units.
- 40 4. A composition according to claim 3, wherein the mutual weight ratio between isoprene and butadiene is in the range of from 48/52 to 52/48.
- 45 5. A composition according to claim 1, wherein component (b) occurs in a weight proportion of from 8 to 12 wt%.
6. A composition according to claim 1, wherein component (b) is selected from poly(styrene), poly ethylene, polypropylene or copolymers of ethylene and propylene.
- 50 7. A composition according to claim 1, wherein the component (c) occurs in a weight proportion of from 4 to 6 wt%.
8. A composition according to claim 1, wherein the component (a) comprises poly(styrene) blocks S, having a true molecular weight in the range of from 10,500 to 15,000, and said block copolymer has an apparent molecular weight of from 115,000 to 155,000, and has a poly(styrene) content of from 29 to 30 %, and has a diblock S-(I/B) content of from 0 to 15 mole%.
- 55 9. Extruded mono- or multi-layer films prepared from the compositions according to claims 1-8.

10. Cast or blown mono- or multi-layer films for personal hygiene applications, prepared from the compositions according to claims 1-8.

5 **Patentansprüche**

1. Zusammensetzung zur Verwendung für die Herstellung von transparenten, gelfreien Folien, umfassend:

a) wenigstens 65 Gew.-% eines Styrolblockcopolymers, das eine Molekularstruktur gemäß der Formel



aufweist, worin jedes S unabhängig voneinander ein Polymerblock aus überwiegend Styrol ist und (I/B) ein im Wesentlichen Zufallspolymerblock aus überwiegend Isopren und Butadien in einem wechselseitigen Gewichtsverhältnis im Bereich von 30/70 bis 70/30 ist, und worin der Polymerblock (I/B) eine Glasübergangstemperatur (T_g) von maximal -60°C aufweist (bestimmt gemäß ASTM E-1356-98), und worin n eine ganze Zahl gleich oder größer 2 ist, und worin X der Rest eines Kopplungsmittels ist, und worin das Styrolblockcopolymer einen Poly(styrol)gehalt im Bereich von 28 bis 31 Gew.% aufweist, und Poly(styrol)blöcke S eines wahren Molekulargewichts im Bereich von 10.000 bis 15.000 hat und ein scheinbares Molekulargewicht des gesamten Blockcopolymers im Bereich von 110.000 bis 160.000 aufweist, und worin der Diblock S - (I/B) wahlweise in einem Gehalt von maximal 20 mol% auftritt,

b) von 5 bis 25 Gew.-% eines zweiten thermoplastischen Harzes,

c) von 0 bis 10 Gew.-% eines plastisch machenden Öls, wobei die Summe der Prozente der Bestandteile a),

b) und c) 100% ist und sich alle Gewichtsprozentangaben auf das Gewicht der gesamten Zusammensetzung beziehen.

2. Zusammensetzung nach Anspruch 1, worin der Bestandteil (a) in einem Gewichtsverhältnis von 70 bis 90 Gew.-% auftritt.

3. Zusammensetzung nach Anspruch 1, worin der Polymerblock (I/B) eine Durchschnittshomopolymerblocklänge PB bzw. PI von weniger als 100 Monomereinheiten aufweist, vorzugsweise weniger als 50 Monomereinheiten, und am meisten bevorzugt weniger als 20 Monomereinheiten.

4. Zusammensetzung nach Anspruch 3, worin das wechselseitige Gewichtsverhältnis zwischen Isopren und Butadien im Bereich von 48/52 bis 52/48 liegt.

5. Zusammensetzung nach Anspruch 1, worin Bestandteil b) in einem Gewichtsverhältnis von 8-12 Gew.-% auftritt.

6. Zusammensetzung nach Anspruch 1, worin der Bestandteil b) ausgewählt ist aus Poly(styrol), Polyethylen, Polypropylen oder Copolymeren aus Ethylen und Propylen.

7. Zusammensetzung nach Anspruch 1, worin der Bestandteil c) in einem Gewichtsverhältnis von 4 bis 6 Gew.-% auftritt.

8. Zusammensetzung nach Anspruch 1, worin der Bestandteil a) Poly(styrol)blöcke S umfasst, die ein wahres Molekulargewicht im Bereich von 10.500 bis 15.000 aufweisen und das Blockcopolymer ein scheinbares Molekulargewicht von 115.000 bis 155.000 hat und einen Poly(styrol)gehalt von 29 bis 30% und einen Diblock S - (I/B) - Gehalt von 0 bis 15 mol% aufweist.

9. Extrudierte Mono- oder Mehrschichtfolien hergestellt aus den Zusammensetzung nach den Ansprüchen 1 bis 8.

10. Gegossene oder blasgeformte Mono- oder Mehrschichtlagenfolien für persönliche Hygieneanwendungen, hergestellt aus den Zusammensetzungen nach den Ansprüchen 1 bis 8.

55 **Revendications**

1. Composition à utiliser pour la fabrication de films exempts de gel, transparents, comprenant :

- a) au moins 65 % en poids d'un copolymère bloc styrénique, ayant une structure moléculaire répondant à la formule :
 $S-(I/B)-S$ (1) ou $[S-(I/B)]_n X$ (2),
 dans lesquelles chaque S représente indépendamment un bloc de polymère essentiellement de styrène et (I/B) est un bloc de polymère sensiblement aléatoire essentiellement d'isoprène et de butadiène dans un rapport en poids mutuel allant de 30/70 à 70/30, dans lequel ledit bloc de polymère (I/B) a une température de transition vitreuse (Tg) d'au plus -60°C (déterminée suivant ASTM E-135-98), dans laquelle n est un nombre entier égal ou supérieur à 2, et dans laquelle X est le résidu d'un agent de couplage, ledit copolymère bloc styrénique ayant une teneur en poly(styrène) allant de 28 à 31 % en poids, comportant des blocs de poly(styrène) S d'un poids moléculaire réel allant de 10 000 à 15 000, ayant un poids moléculaire apparent du copolymère bloc complet allant de 110 000 à 160 000 et dans laquelle le dibloc S-(I/B) se produit éventuellement à une teneur d'au plus 20 moles %,

 b) de 5 à 25 % en poids d'une seconde résine thermoplastique,

 c) de 0 à 10 % en poids d'une huile plastifiante, la somme des pourcentages des composants a, b et c étant 100 %, et tous les pourcentages en poids étant pris par rapport au poids de la composition complète.
2. Composition suivant la revendication 1, dans laquelle le composant (a) se produit dans une proportion pondérale de 70 à 90 % en poids.
 3. Composition suivant la revendication 1, dans laquelle le bloc de polymère (I/B) a une longueur de bloc d'homopolymère moyenne PB, respectivement PI de moins de 100 unités de monomère, avantageusement moins de 50 unités de monomère, et plus avantageusement de moins de 20 unités de monomère.
 4. Composition suivant la revendication 3, dans laquelle le rapport en poids mutuel entre l'isoprène et le butadiène se situe dans la plage de 48/52 à 52/48.
 5. Composition suivant la revendication 1, dans laquelle le composant (b) se produit dans une proportion pondérale de 8 à 12 % en poids.
 6. Composition suivant la revendication 1, dans laquelle le composant (b) est choisi parmi le poly(styrène), le polyéthylène, le polypropylène et les copolymères d'éthylène et de propylène.
 7. Composition suivant la revendication 1, dans laquelle le composant (c) se produit dans une proportion pondérale de 4 à 6 % en poids.
 8. Composition suivant la revendication 1, dans laquelle le composant (a) comprend des blocs de poly(styrène) S, ayant un poids moléculaire réel allant de 10 500 à 15 000, et le copolymère bloc précité a un poids moléculaire apparent de 115 000 à 155 000, et a une teneur en poly(styrène) de 29 à 30 %, et a une teneur en dibloc S-(I/B) de 0 à 15 moles %.
 9. Films mono- ou multicouches extrudés préparés à partir des compositions suivant l'une quelconque des revendications 1 à 8.
 10. Films mono- ou multicouches coulés ou soufflés pour des applications d'hygiène personnelle, préparés à partir des compositions suivant l'une quelconque des revendications 1 à 8.